

Planejamento de Custos de Produção

REALFIX

REALFIX COLOMBO

Nível	M A T E R I A L		Un	Quantidade	Valor Peças	Valor Unit.	Valor Sub.Contr	Valor MOB	Valor Total	% Na Fórmula
1	026PR008	REALTERM 26 600°C PRETO	KG	100,00000					1.955,391630	
2	P-70	BARISOLV W-018	KG	15,00000	279,510000	18,6340				15,0000
2	G-388	SOLSPERSE M388	KG	0,60000	97,260000	162,1000				0,6000
2	P-60	R SILICONE DC 805	KG	6,65000	673,911000	101,3400				6,6500
2	F-58	BENTONITA ATIVADA	KG	0,90000	18,972000	21,0800				0,9000
2	F-51	MONARCH 570 NEGRO FUMO	KG	1,50000	32,024550	21,3497				1,5000
2	F-47	OXIDO DE FERRO PRETO	KG	8,00000	208,000000	26,0000				8,0000
2	F-41	SYLOID CP280 / GASIL HP270	KG	1,50000	44,115000	29,4100				1,5000
2	F-18	QUARTZO MICRONIZADO OB 6250 # 500	KG	16,10000	45,160500	2,8050				16,1000
2	F-227	SILICA AMORFA PIROGENICA HIDROFILICA HDK KG		0,20000	10,003580	50,0179				0,2000
2	S-06	XILOL	KG	11,60000	93,960000	8,1000				11,6000
2	S-06	XILOL	KG	6,90000	55,890000	8,1000				6,9000
2	P-409	RESINA ÓLEO FENOLADO BF 2450	KG	6,50000	197,730000	30,4200				6,5000
2	S-07	TOLUOL	KG	13,00000	105,300000	8,1000				13,0000
2	S-06	XILOL	KG	11,00000	89,100000	8,1000				11,0000
2	S-07	TOLUOL	KG	0,55000	4,455000	8,1000				0,5500
Custo Total Para Produção					1.955,3916				1.955,391630	
Custo de Venda										
Custo Total					1.955,3916				1.955,391630	